

TEST REPORT

No. : GP090200135-4.2

Date : Feb 06, 2009

Page: 1 of 2

CD FLEXI-VALVE CORPORATION

1/F NO.15 BUILDING, 333 GONGYEZHONG 1/F, NO, 15 BUILDING, 333 ROAD GUANGZHOU, CHINA


The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : CD 3" BSP BUTTERFLY WITH ELBOW ET30M30S07
Material : Polypropylene + 20% Glass Fiber
Test Performed : Selected test(s) as requested by applicant
Date of Receipt : Jan 07, 2009
Test Period : Jan 07, 2009 to Jan 23, 2009

Test result(s) : Please refer to the following page(s)

*****To be continued*****

Signed for and on behalf of
SGS-CSTC Ltd.



May Huo
Engineer

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at <http://www.sgs.com/terms-and-conditions.htm>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.

GZMR 009690

TEST REPORT

No. : GP090200135-4.2

Date : Feb 06, 2009

Page: 2 of 2

Test Result(s):

Sample description: see photo


Test part	Test item(s)	Test method	Test result ,mg/L	Unit	limitation
silicon rubber part	Evaporated residue (65% ethanol immersion)	GB/T 5009.60-2003	19	mg/L	≤40
	Evaporated residue (4% acetic acid immersion)		15.5	mg/L	≤2000
	Potassium permanganate consumption		1.27	mg/L	≤40
	Zinc(Zn)	GB/T 5009.64-2003	< 10	mg/L	≤20
	Evaporated residue (n-hexane immersion)	GB/T 5009.60-2003	599	mg/L	≤2000
metal part	Leached Pb contents	GB/T 5009.81-2003	0.08	mg/L	< 1.0
	Leached Cr contents		0.10	mg/L	< 0.5
	Leached Ni contents		0.06	mg/L	< 3.0
	Leached Cd contents		< 0.01	mg/L	< 0.02
	Leached As contents		< 0.01	mg/L	< 0.04
PP part	Evaporated residue (4% acetic acid immersion)	GB/T 5009.60-2003	17	mg/L	≤30
	Evaporated residue (n-hexane immersion)		26	mg/L	≤30
	Potassium permanganate consumption		0.64	mg/L	≤10
	Heavy metal (Pb)		< 1	mg/L	≤1
	Decolor test (immersion)		negative	—	negative

Conclusion: the test results of the submitted samples were conformed to the GB 4806.1-1994, GB 9684-1988 and GB 9688-1988.

Note: 1. The results of this report were copied from the report No.GP090100046-2.2

2. The above test has been subcontracted to the accredited laboratory.

Sample photo:



*****End of report*****

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at <http://www.sgs.com/termsandconditions.htm>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) listed and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.